
























Product Information


Technical Data Sheet

Intensity Of Use	ISO 10874			23 High Domestic 33 High Commercial	Class
Total Thickness	EN ISO 24346			3.00	mm
Wear Layer	EN ISO 24340			0.50 (PU Wear Layer)	mm
Abrasion Group	EN 660-2			I	Class
Total Weight	EN ISO 23997 (EN 430)			2198	g/m ²
Standard Width	EN ISO 24341 (EN 426)			2 - 4	mtr
Standard Length	EN ISO 24341 (EN 426)			+/- 20	mtr
Commercial Warranty				5	Years

Technical Information

Dimensional Stability	EN ISO 23999 (EN 434)			≤ 0.40	%
Curling	EN ISO 23999			≤ 8	mm
Light Stability	EN ISO 105 B02			≥ 6-7	Degree
Residual Indent	EN ISO 24343-1 (EN 433)			≤ 0.20	mm
Impact Sound Improvement	EN ISO 717/2			△ Lw 18	dB
Dynamic Coefficient of Friction	EN 13893			DS	
Slip Resistance	DIN 51130			R10	Scale
Reaction to Fire	EN 13501-01			Bfl-s1	Class
Underfloor Heating	EN 12667			Suitable	
Thermal Resistance	EN ISO 12664			0.0275	m ² K/w
Thermal Conductivity	EN 10456			0.25	W/m.k
Chemical Resistance	EN ISO 26987			Very Good	
Static Electrical Propensity	EN 1815			< 2kV	
Furniture Leg Resistance	ISO 16581 (EN424)			Very Good	
Castor Chair Resistance	EN ISO 12529			Suitable (Type Wheel W)	Very Good
Welding				Available	Hot / Cold

Environment

- 
- No heavy metals
 - No solvents
 - No Formaldehydes
 - No harmful plasticizers
- 100% Recyclable.

Slovenian plant Slovenian / Belgium plant

