















Product Information

Technical Data Sheet

Sand 592

Intensity Of Use	ISO 10874 (EN 685)		22 General Domestic	Class
Total Thickness	EN ISO 24346 (EN 428)		2.80	mm
Wear Layer	EN ISO 24340 (EN 429)		0.20	mm
Total Weight	EN ISO 23997 (EN 430)		1600	g/m ²
Standard Width	EN ISO 24341 (EN 426)		2 - 4	mtr
Standard Length	EN ISO 24341 (EN 426)		+/- 20	mtr
Residential Warranty			5	Year

Technical Information

Impact Sound Improvement	EN ISO 717/2		△ Lw 18	dB
Dynamic Coefficient of Friction	EN 13893		DS	
Slip Resistance	DIN 51130		R10	Scale
Reaction to Fire	EN 13501-01		Cfl-s1	Class
Underfloor Heating	EN 12667		Suitable	
Thermal Resistance	ISO 8302		0.0112	m ² K/w
Thermal Conductivity	EN 12524		0.25	W/m.k
Chemical Resistance	ISO 26987 (EN423)		Resistant	

E1

APPROVED
FOR
EMISSIONS

E1 means that the level of formaldehyde is inferior to 0.1ppm (= 0.12 mg/m³ of air)

Environment



100% Recyclable.

- No heavy metals
- No solvents
- No Formaldehydes
- No harmful plasticizers

