


















Product Information

Technical Data Sheet

Intensity Of Use	ISO 10874 (EN 685)		23 Heavy Domestic 31 Moderate Commercial	Class
Total Thickness	EN ISO 24346 (EN 428)		3.00	mm
Wear Layer	EN ISO 24340 (EN 429)		0.25	mm
Total Weight	EN ISO 23997 (EN 430)		1840	g/m ²
Standard Width	EN ISO 24341 (EN 426)		2, 3, 4	mtr
Standard Length	EN ISO 24341 (EN 426)		+/- 20	mtr
Residential Warranty			10	Years

Technical Information

Dimensional Stability	EN ISO 23999 (EN 434)		≤ 0.20	%
Light Stability	EN ISO 105 B02		≥ 6	Degree
Residual Indent	EN ISO 24343-1 (EN 433)		≤ 0.18	mm
Impact Sound Improvement	EN ISO 717/2		△ Lw 20	dB
Formaldehyde Emission	EN 717-1		E1 HCHO	
Slip Resistance	DIN 51130		R10	Scale
Reaction to Fire	EN 13501-01		Cfl-s1	Class
Underfloor Heating	EN 12667		Suitable	
Thermal Resistance	ISO 8302		0.05	m ² K/w
Chemical Resistance	ISO 26987 (EN423)		Resistant	
Static Electrical Propensity	EN 1815		< 2kV	On Concrete

